



TECHNICAL DATA SHEET

TECHNICAL DATA SHEET

DOD-24607A

NON-FLAMING (INTUMESCENT) ENAMEL

- PRODUCT:** A government specification, non-flaming enamel formulated to meet DOD-24607A.
- DESCRIPTION:** **DOD-24607A NON-FLAMING ENAMEL** is an intumescent, non-flaming coating that is resistant to burning and flaming.
- PROPERTIES:** COLORS..... Per Fed-Std 595B
FINISH..... Semigloss
SOLIDS(Weight)..... 79- 82%
PIGMENT(Weight)..... 52 - 54%
VISCOSITY..... 80 - 90 KU
- DRYING TIMES:**
TO TOUCH..... 2 Hours
DRY HARD..... 5 hours
- ADVANTAGES:** (1). Non-Flaming (intumescent) Properties
(2). Meets DOD-24607A
(3). Resistant to Burning
(4). Air Dry-Semigloss Finish
- USES:** (1). Aerospace Applications
(2). Submarines
(3). Factories
(4). Industrial Facilities
- APPLICATION:** Apply by brush, roller or spray methods. For brush and roll, thin with Mineral Spirits Reduce at 10% by volume. For spray application, thin with Xylene at 10-15% by volume. Apply to a dry film thickness of 1.5 - 2.0 mils.

PRECAUTIONS:

KEEP OUT OF REACH OF CHILDREN.
USE WITH ADEQUATE VENTILATION.
AVOID CONTACT WITH SKIN AND EYES.
READ MATERIAL SAFETY DATA SHEET BEFORE USING.
CONTENTS ARE FLAMMABLE.